

Co-60 1200 Kev	% original beam strength reduction			
Thickness (inch)	Tungsten	Bismuth	Stainless/Mag	Iron
1/8	13	12	7	4
1/4	25	21	12	9
3/8	35	30	17	14
1/2	43	38	21	18
5/8	50	45	25	22
3/4	55	51	29	26
7/8	60	56	33	30
1	65	61	37	34
1 1/8	69	65	41	38
1 1/4	73	69	45	42
1 3/8	77	72	48	45
1 1/2	81	75	51	48
1 5/8	84	78	54	51
1 3/4	86	80	56	53
1 7/8	88	81	58	55
2	89	82	59	56
Half Value Layer	0.63"	0.78"	1.45"	1.66"
Tenth Value Layer	2.09"	2.62"	4.81"	5.51"

