

Co-60 1200 Kev	% original beam strength reduction		
Thickness (inch)	Tungsten	Bismuth	Iron
1/8	13	12	4
1/4	25	21	9
3/8	35	30	14
1/2	43	38	18
5/8	50	45	22
3/4	55	51	26
7/8	60	56	30
1	65	61	34
1 1/8	69	65	38
1 1/4	73	69	42
1 3/8	77	72	45
1 1/2	81	75	48
1 5/8	84	78	51
1 3/4	86	80	53
1 7/8	88	81	55
2	89	82	56
Half Value Layer	0.63"	0.78"	1.66"
Tenth Value Layer	2.09"	2.62"	5.51"

