

Co-60 1200 Kev	% original beam strength reduction			
Thickness (inch)	Tungsten	Bismuth	Stainless	Iron
1/8	13	12	7	4
1/4	25	21	13	9
3/8	35	30	19	14
1/2	43	38	24	18
5/8	50	45	28	22
3/4	55	51	32	26
7/8	60	56	35	30
1	65	61	39	34
1 1/8	69	65	43	38
1 1/4	73	69	46	42
1 3/8	77	72	49	45
1 1/2	81	75	52	48
1 5/8	84	78	55	51
1 3/4	86	80	57	53
1 7/8	88	81	59	55
2	89	82	61	57
Half Value Layer	0.63"	0.78"	1.45"	1.61"
Tenth Value Layer	2.09"	2.62"	4.81"	5.51"

